

OK Autrod 308LSi

A continuous solid corrosion resisting chromium-nickel wire for welding of austenitic chromium nickel alloys of 18% Cr - 8% Ni-type.

OK Autrod 308LSi has a good general corrosion resistance. The alloy has a low carbon content which makes this alloy particularly recommended where there is a risk of intergranular corrosion. The higher silicon content improves the welding properties, such as wetting. The alloy is widely used in the chemical and food processing industries as well as for pipes, tubes and boilers.

Классификации	AWS A5.9 : ER308LSi EN ISO 14343-A : G 19 9 LSi
Одобрения	DNV 308L (до -196 °C)

Одобрения на материалы выдаются с привязкой к заводу изготовителю. Подробную информацию можно получить в представительствах ESAB.

Тип сплава	Austenitic (with approx. 8 % ferrite) 19% Cr - 9% Ni - Low C - High Si
Защитный газ	M12, M13 (EN ISO 14175)

Механические свойства при растяжении

Состояние	Предел текучести	Предел прочности при растяжении	Удлинение
После сварки	420 MPa	570 MPa	36 %
Tested at 350°C.			

Типичные свойства образца с V-образным надрезом по Шарпи

Состояние	Температура испытания	Работа удара
M12 (98%Ar + 2%CO2) или M13 (98%Ar + 2%O2)		

Хим. состав наплавленного металла

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
0.03	1.8	0.7	0.009	0.020	10.0	19.5	0.03	0.1	0.04

Хим. состав наплавленного металла

Nb	FN WRC-92
0.01	6

Хим. состав проволоки

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
0.01	1.8	0.8	0.012	0.013	10.0	20.0	0.1	0.10	0.06

Хим. состав проволоки

Nb	FN WRC-92
0.02	8

Данные наплавки

Диаметр	Ток	В	Скорость подачи проволоки	Коэфф. наплавки
0.8 mm	55-160 A	15-24 V	4.0-17.0 m/min	1.0-4.1 kg/h
0.9 mm	65-220 A	15-28 V	3.5-18.0 m/min	1.1-5.4 kg/h
1.0 mm	80-240 A	15-28 V	4.0-16.0 m/min	1.5-6.0 kg/h
1.2 mm	100-300 A	15-29 V	3.0-14.0 m/min	1.6-7.5 kg/h
1.6 mm	230-375 A	23-29 V	5.5-9.0 m/min	5.2-8.6 kg/h

Данные наплавки

Диаметр проволоки
0.6 mm
1.14 mm